

Article

Mechanical Enhancement of Biodegradable Poly(Butylene Succinate) by Biobased Polyamide11

Nattakarn Hongsrphan^{a,*}, Chanasit Kaew-ngam^b, Ploypailin Saengdet^c, and Nisachon Kongtara^d

Department of Materials Science and Engineering, Faculty of Engineering and Industrial Technology, Silpakorn University, Nakhon Pathom, 73000, Thailand

E-mail: ^aHongsrphan_N@su.ac.th (Corresponding author), ^bChanasit_ice@hotmail.com, ^cPloypailin.s_s18@vistec.ac.th, ^dNisachonkongtaranini@gmail.com

Abstract. Biodegradable poly(butylene succinate) (PBS) was melt blended with biobased polyamide11, which an epoxy-based chain extender, Joncryl ADR-4300, was added to improve the blend compatibility. Mechanical properties of the blends were evaluated by tensile and impact testing. The blends were characterized by Fourier transform infrared spectroscopy, Differential scanning calorimetry and Thermogravimetric analysis. Morphology was investigated by Scanning electron microscopy. It was found that morphology of the immiscible blends with polyamide11 less than 50 wt% was a sea-island structure. Adding the chain extender confirmed better chemical compatibility in the blends evident by smaller dispersed domain sizes and less pullout. The blends with higher polyamide11 content increased Young's modulus following the rule of mixture, however, the rigidity was reduced when adding the chain extender. It was interesting to observe that impact strength of the blends with polyamide11 content higher than 30 wt% was enhanced significantly with the presence of chain extender, although tensile strength and elongation at break were reduced. The crystallization temperature of PBS increased with higher polyamide11 content due to the nucleation effect, although the degree of crystallinity was in the same range. The thermal degradation temperature of the blend was shifted to higher temperature confirming the chain extension reaction occurred.

Keywords: Poly(butylene succinate); polyamide11; chain extender; morphology.

ENGINEERING JOURNAL Volume 25 Issue 2

Received 7 February 2020

Accepted 25 November 2020

Published 28 February 2021

Online at <https://engj.org/>

DOI:10.4186/ej.2021.25.2.295

This article is based on the presentation at the International Conference on Engineering and Industrial Technology (ICEIT 2020) in Chonburi, Thailand, 11th-13th September 2020.

Table 1 summarizes abbreviation and composition of samples prepared and tested in the research. The melt blending was carried out in a co-rotating twin-screw extruder (SHJ-25, Yongteng, China) using a screw speed of 40 rpm. The barrel/die temperature profile was set at 140-150-160-160-170-185-190-200°C. The extrudate was water cooled, pelletized, and dried in an air-circulating oven (Model FD53, Binder, Germany) at 70°C for 5 hours. Dried pellets were kept in zip-lock plastic bags and stored in a sealed plastic box equipped with silica gel bags to prevent moisture pick-up. Dogbone specimens (ASTM-D638 Type I, a narrow-section width of 12.8 mm and a thickness of 3.25 mm) and rectangular specimens (ASTM-D790, a length of 126.5 mm, a width of 12.5 mm and a thickness of 3.25 mm) were fabricated using an injection molding machine (BA250CDC, Battenfeld, UK). Neat PBS, neat nylon11, and the PBS/nylon11 blend specimens were fabricated using the barrel/nozzle temperature about 200-210°C, while neat nylon11 specimens had to be fabricated at 240°C.

Table 1. Abbreviation and composition of samples.

Abbreviation	PBS (wt%)	Nylon11 (wt%)	Joncryl ADR-4300 (phr)
P100	100	0	-
P9N1	90	10	-
P8N2	80	20	-
P7N3	70	30	-
P6N4	60	40	-
P5N5	50	50	-
N100	0	100	-
P9N1J0.5	90	10	0.5
P8N2J0.5	80	20	0.5
P7N3J0.5	70	30	0.5
P6N4J0.5	60	40	0.5
P5N5J0.5	50	50	0.5
P9N1J1.0	90	10	1.0
P8N2J1.0	80	20	1.0
P7N3J1.0	70	30	1.0
P6N4J1.0	60	40	1.0
P5N5J1.0	50	50	1.0

2.3. Characterization and Testing

Morphology of cryo-fractured specimens was examined using a Scanning electron microscope (SEM, TM3030, Hitachi, Japan). The fractured surface was gold/platinum coated prior to inspection to avoid electrostatic charging. The gold/platinum coating was performed by a sputter coater (Model SC7620, Quorum Technologies, UK) using a testing condition that used an electricity input of 20 mA, a pressure of 10⁻¹ mBar and a sputtering time of 45 second.

Neat PBS, neat nylon11, Joncryl ADR-4300, and PBS/nylon11 blends were characterized functional groups by a Fourier transform infrared spectrometer (FTIR, VERTEX70, Bruker, USA). Pellets and KBr powder were dried thoroughly in an air-circulating oven (Model FD53, Binder, Germany). Then, they were mixed in the weight

ratio of 1:9 (sample:KBr) and pressed by a hydraulic presses (Model 3392, Carver Inc., USA) using a hydraulic pressure of 10,000 Bar for 2 mins to obtain KBr discs for characterization.

Tensile properties of neat PBS, neat nylon11, and PBS/nylon11 blends were evaluated in accordance to ASTM-D638 using a universal testing machine (Model 5969, Instron Engineering Corporation, USA). The tests were carried out using a crosshead speed of 50.8 mm/min. Ten specimens were tested, which the averages and standard deviations of Young's modulus, tensile strength, and elongation at break were calculated.

Impact strength of neat PBS, neat nylon11, and PBS/nylon11 blends was determined in accordance to ASTM-D256 (notched Izod impact test) using an impact tester (Ceast 9050 Pendulum Impact System, Instron Engineering Corporation, USA). The pendulum weight was 25 Joule. Ten specimens were tested which the averages and standard deviations of impact strength were calculated.

Thermal property analysis of neat PBS, neat nylon11, and PBS/nylon11 blends was evaluated using a differential scanning calorimeter (Pyris 1, Perkin Elmer, USA) under nitrogen atmosphere. Sample weight was about 5-10 mg. The samples were tested in a heat-cool-reheat mode. Temperature scan was performed from 50°C to 200°C with a heating rate and a cooling rate of 10°C/min. The crystal melting temperatures (T_m) and the crystallization temperatures (T_c) were reported. The degree of crystallinity (X_c) was calculated using Eq. (1).

$$\%X_c = \frac{\Delta H_m}{\Delta H_m^0} \times \frac{100}{w} \quad (1)$$

where w was weight fraction of PBS or nylon11 in the composite, ΔH_m was melting enthalpy of sample (J/g), and ΔH_m^0 was either melting enthalpy of 100% crystalline PBS (110.3 J/g) [7] or of 100% crystalline nylon11 (206 J/g) [8].

Thermal stability analysis of neat PBS, neat nylon11, and the PBS/nylon11 blends was evaluated using a Thermogravimetric analyzer (TGA7, Perkin Elmer, USA) under nitrogen atmosphere. Sample weight was about 5-10 mg. Temperature scan was performed from 50°C to 600°C with a heating rate of 10°C/min.

3. Results and Discussion

3.1. Morphological Study of PBS/Nylon11 Blends

Since PBS (polyester) and nylon11 (polyamide) are condensation polymers with different functional groups, the blend has a tendency to be an immiscible blend. The addition of an epoxy-based chain extender such as Joncryl ADR-4300 having six epoxy functionalities per polymer chain, could introduce the partial-miscibility through the chain extension reaction among these polymer molecules. Figure 2 shows SEM micrographs of the PBS/nylon11 blends in various weight ratios adding 0, 0.5, and 1.0 phr of Joncryl ADR-4300. From SEM micrographs, it is clearly seen that the PBS/nylon11 blends without Joncryl ADR-4300 are an immiscible blend at which nylon11 are

dispersed phases due to the lesser weight fraction. According to MFIs by the suppliers, it should be noted that nylon11 melt is much more viscous than PBS melt under the compounding condition at 200°C. When the weight ratio of nylon11 is higher than 30 wt%, the domain size of the dispersed phases is observed to be bigger at which a domain size of >30 µm can be seen. This is attributed to the limitation of the applied shearing stress that could not transfer effectively from the PBS matrix to break the viscous nylon11 dispersed phases. Compared with the work by Lorenzo *et al.* [9] using the blending temperature of 210°C, the main matrix was polyamide11 at which the sizes of PBS dispersed phases increased with higher PBS content. The morphology of the PBS/nylon11 50/50 wt% blend is co-continuous that the nylon11 phases are elongated and embedded inside the PBS main matrix.

Nevertheless, there are voids between PBS matrix and nylon11 domains, which the pullout of nylon11 domains during the impact fracture is observed indicating ineffective interfacial adhesion between polymer phases if there is any. Whitening edges are observed around the empty pits implying there is stretching of the main matrix somewhat occurred before the pullout is complete. This is attributed to the possible interfacial interaction between the matrix and the dispersed phases. Due to the work by Lorenzo *et al.* [9], they observed there was small fibrils bonded between PBS domains and the polyamide11 matrix, but there were voids among the surface bonding. They suggested that the interaction between functional groups of polyamide11 and PBS phases. In the other words, the transesterification possibly occurred between polyamide11 and PBS phases.

Interestingly, for the PBS/nylon11 60/40 wt% blend, the domain sizes are smaller than those in the PBS/nylon11 70/30 wt% blend. This implies that the nylon11 domain sizes in this weight ratio blend are too large to be stable with the balance between surface tension and applied shear stress. Thus, they are stretched by shear stress and broken into smaller domain sizes during the melt compounding. On the other hand, the viscous nylon11 phases could form continuous phase which the PBS domains are distributed inside the matrix.

Clearly, adding Joncryl ADR-4300 into the PBS/nylon11 blends improves the compatibility among polymer molecules. This indicates by the nylon11 domains of the blends adding Joncryl ADR-4300 are smaller than the blends without this chain extender at the same weight ratio of nylon11 content. Moreover, most of the nylon11 domains embedded firmly inside the PBS matrix with just a few domains are pulled out after the impact failure. This is similarly to the work by Zhou *et al.* [10]. Since Joncryl ADR-4300 could initiate the chain extension reaction between PBS polyester molecules that eventually increases the molecular weight and thus increases melt viscosity of the PBS matrix as well. When the difference of melt viscosities is reduced, the dispersed phases are able to be stretched easier by the applied shear stress and thus are broken into smaller domains distributed inside the PBS main matrix.




Fig. 2. SEM micrographs (magnification of 2000X) of impact fracture surfaces of PBS/nylon11 blends adding Joncryl ADR-4300.

3.2. FTIR Characterization of Neat PBS, Neat Nylon11, and the PBS/Nylon11 Blends with or Without Joncryl ADR-4300

Figure 3 presents FTIR spectra of neat PBS, neat nylon11, and Joncryl ADR-4300. For PBS polyester, the main characteristic FTIR spectra occurs at 3437.46 cm^{-1} attributed to the O-H stretching of the PBS's end groups, at 2954.23 cm^{-1} attributed to the C-H stretching, at 1725.27 cm^{-1} attributed to the C=O stretching, and at 1725.27 cm^{-1} attributed to the C-O-C stretching. For nylon11 polyamide, the main characteristic FTIR spectra occurs at 3304.36 cm^{-1} attributed to the -NH stretching, at 2925.34 and 2854.17 cm^{-1} attributed to the -CH stretching, at 1549.58 cm^{-1} attributed to the -NH bending, and at 1644.21 cm^{-1} attributed to the C=O stretching. For Joncryl ADR-4300, the wavenumbers at 1183.95, 905.93 (epoxy ring), and 757.68 cm^{-1} are attributed to the C=O stretching, and the wavenumber at 1729.18 cm^{-1} is attributed to the C=O stretching. The wavenumber between 3024.01 and 2929.10 cm^{-1} is attributed to the -CH stretching. Thus, these spectra confirm that Joncryl ADR-4300 is an epoxidized ester.

For the FTIR spectra of the PBS/nylon11 blends, it is found that the FTIR spectra of the samples without Joncryl ADR-4300 were similar to those of neat PBS and neat nylon11 without any shifting. This implies that the PBS and nylon11 phases do not chemically interact to form covalent bonding between them, only having weak physical interaction via hydrophilicity of the functional groups if there is any. This correlates to the morphology of

the blends without Joncryl in SEM micrographs that the voids between phases are present. For the blends adding Joncryl ADR-4300, the spectrum of epoxide rings could not be observed, which possibly results from only small concentration of the chain extender adding into the blends. Also, it might indicate that they had already reacted with PBS and nylon11 molecules resulting in the better compatibility of the reactive blends as evident in SEM micrographs. The chemical reaction between PBS and nylon11 via Joncryl ADR-4300 is proposed as shown in Fig. 4.




Fig. 3. The FTIR spectra of neat PBS (a), neat nylon11 (b), and Joncryl ADR-4300 (c).




Fig. 4. The chemical reaction scheme between PBS and nylon11 with the presence of Joncryl ADR-4300.

3.3. Tensile Properties of the PBS/Nylon11 Blends

Figure 5 presents Young's modulus of neat PBS and the PBS/nylon11 blends as a function of nylon11 content. Young's modulus of neat PBS and neat nylon11 are 242.99 ± 1.96 and 472 ± 12.70 MPa, respectively. The red line represents the rule of mixture that calculates Young's modulus based on the modulus of neat polymer and their weight ratios as described in Eq. (2).

$$E_{\text{blend}} = E_{\text{PBS}}W_{\text{PBS}} + E_{\text{nylon11}}W_{\text{nylon11}} \quad (2)$$

It was seen that Young's modulus of mostly blends without Joncryl ADR-4300 was following the rule of mixture. However, the PBS/nylon11 60/40 wt% blend had higher Young's modulus than the calculated value. Since the domain sizes of the PBS/nylon11 60/40 wt% were smaller than that of the PBS/nylon11 70/30 wt% under the same mixing condition, the smaller dispersed phases of nylon11 with higher content became the reinforcing fillers in the PBS matrix. Since the interfacial interaction between the PBS matrix and the nylon11 dispersed phases is observed in SEM micrograph, the load transfer from the softer main matrix to the more rigid dispersed phases could be achieved. However, adding Joncryl ADR-4300 as a chain extender did not increase the rigidity of the blends although the better compatibility between phases was introduced which the finer dispersed phases embedded inside the PBS matrix with less voids.




Fig. 5. Young's modulus of neat PBS and the PBS/nylon11 blends as a function of nylon11 content.




Fig. 6. Tensile strength of neat PBS and the PBS/nylon11 blends as a function of nylon11 content.




Fig. 7. Elongation at break of neat PBS and the PBS/nylon11 blends as a function of nylon11 content.

Figure 6 and 7 present tensile strength and elongation at break of neat PBS and the PBS/nylon11 blends as a function of nylon11 content, respectively. Similarly, the rule of mixture was applied and the red line represented the values of tensile strength of the blends that followed the rule. Clearly, the tensile strength of the blends was lower than the calculated values. This emphasized on the immiscibility between PBS and nylon11 phases. Incorporating Joncryl ADR-4300 into the PBS/nylon11 blends increased the values of the tensile strength attributed to the limited improvement of interfacial interaction between phases. As seen in SEM micrographs, the dispersed phase size of nylon11 was reduced and embedded inside the PBS matrix. This caused the tensile strength to be higher compared to the blends without the chain extender. Nevertheless, the improvement was considered to be limited, since the tensile strength value was still lower than those of both neat PBS and neat nylon11, and elongation at break was much lower than neat polymers. This was due to the possibility of chain scission of PBS molecules caused by the chain extension reaction. Although the reaction did improve the interfacial interaction between phases, the pullout of the dispersed phases in the blends with nylon11 content lower than 30 wt% were still observed.

It was found that the trend of elongation at break was lower for the PBS/nylon11 blends adding 30 wt% nylon with Joncryl ADR-4300. From SEM micrographs, the dispersed phases of nylon11 at the weight ratio of 30 wt% without Joncryl ADR-4300 were the largest due to agglomeration. The size of dispersed phase was reduced significantly after incorporating with Joncryl-4300, and the interfacial adhesion was improved as evident in the increase of tensile strength. Although these dispersed phases were smaller, they were still agglomeration-like compared to the other compositions. Those agglomerated sites became the stress concentrators that the matrix and the dispersed phases were separated due to the higher non-uniform distribution of the domain size.

3.4. Impact Strength of the PBS/Nylon11 Blends

Figure 8 presents impact strength of neat PBS and the PBS/nylon11 blends plotting as a function of nylon11 content. In this study, the neat PBS specimen had an

impact strength of 10.16 ± 3.4 kJ/m² while the neat nylon11 had an impact strength of 10.67 ± 0.34 kJ/m². Since the values of impact strength of these polymers were closed in values, the impact strength of the blends theoretically would not be different from the neat polymers as shown in the rule of mixture (red line). However, the massive reduction of impact strength was observed when the blends consisted of nylon11 less than 20 wt%. In addition, adding Joncryl ADR-4300 into the blends in these weight ratios did not improve the impact strength of the blends. This results emphasized effect of stress concentration introduced by those small dispersed phases of nylon11 that allowed crack propagation to occur in the blends easier compared to neat polymer. When the nylon11 content was 30 wt%, the blend had significant improvement of impact strength. This related to the PBS matrix shrank around these nylon11 domains and generated high physically interfacial adhesion that higher energy was required to break them apart or even pull-out these domains from the main matrix. This was similarly to the work by Moriyama *et al.* [4], which they explained that a larger shrinkage ratio difference between polyamide11 and PBS formed a larger dilational stress field resulting in a higher impact strength. When adding Joncryl, this effect was less dominant due to smaller domain sizes, so that the impact strength was reduced to be in the same range of those of neat polymers.




Fig. 8. Impact strength of neat PBS and the PBS/nylon11 blends as a function of nylon11 content.

3.5. Thermal Property Analysis of Neat PBS and PBS/Nylon11 Blends by DSC

Table 2 presents glass transition temperatures (T_g), crystallinity temperatures (T_c), crystal melting temperatures (T_m), and the degree of crystallinity (X_c). Figures 9 and 10 show crystallization temperatures of PBS and nylon11 phases, and the degree of crystallinity of PBS and nylon11, respectively. Neat PBS showed T_g at -32.5°C which it was not shifted significantly when melt blending with nylon11 with or without the chain extender. It was expected that the T_g would be shifted when the chain extension reaction took place resulting on the linking among molecules or the reduction of molecular weights occurred to allow better

mobility of short-chain molecules. Moreover, the T_m of both polymers showed at the same temperatures of those neat polymers, which indicated there was no presence of the transesterification as reported by Sang-Woo Kim [11]. Nevertheless, the T_c of PBS phase was shifted to higher temperature when blending with nylon11. This implied that nylon11 dispersed phases that crystallized first at

about 163°C acted as the nucleating agents for the PBS molecules to crystallize. The percentage of crystallinity did not differentiate significantly when the nylon11 content was varied. Since the T_m of PBS was still the single peak, this implied the crystal form was similar compared to neat PBS

Table 2. Glass transition temperatures (T_g), crystallization temperatures (T_c), crystal melting temperatures (T_m), and the degree of crystallinity (X_c).

Sample	$T_{g,PBS}$ (°C)	$T_{g,nylon11}$ (°C)	$T_{m,PBS}$ (°C)	$T_{m,nylon11}$ (°C)	$T_{c,PBS}$ (°C)	$T_{c,nylon11}$ (°C)	$X_{c,PBS}$ (%)	$X_{c,nylon11}$ (%)
Nylon11	n/a	59.48	n/a	184.95	-	162.51	n/a	21.66
PBS	-32.52	n/a	113.23	n/a	76.04	-	53.63	n/a
P9N1	-32.45	59.25	113.48	183.35	84.70	165.64	48.41	16.80
P8N2	-32.41	59.08	113.44	183.04	84.22	165.30	49.04	16.14
P7N3	-32.03	58.69	113.97	184.57	83.21	164.03	24.26	6.18
P6N4	-31.88	59.44	115.98	185.38	82.36	163.38	24.99	6.25
P5N5	-32.46	61.11	114.93	184.63	82.61	163.36	44.44	14.62
P9N1_0.5 phr	-32.48	59.35	113.43	183.21	82.27	164.75	49.94	22.09
P8N2_0.5 phr	-32.59	59.32	112.91	182.86	81.68	165.48	54.53	15.68
P7N3_0.5 phr	-32.27	59.58	113.71	183.86	79.93	163.49	46.89	16.62
P6N4_0.5 phr	-32.40	59.92	115.39	184.30	79.90	163.18	49.95	19.67
P5N5_0.5phr	-32.43	59.46	114.55	184.08	80.12	163.06	52.22	21.03
P9N1_1phr	-32.22	59.35	113.19	183.29	79.05	164.57	45.75	14.13
P8N2_1phr	-32.19	59.29	111.97	182.51	75.47	163.30	47.17	16.33
P7N3_1phr	-37.68	59.62	114.74	184.84	77.41	163.42	32.38	11.02
P6N4_1phr	-32.65	57.16	115.11	184.20	80.54	163.48	43.28	13.20
P5N5_1phr	-32.30	59.66	113.55	183.29	80.26	163.54	52.58	18.98




Fig. 9. Crystallization temperatures of PBS and nylon11 phases with and without Joncryl ADR-4300.




Fig. 10. Degree of crystallinity (X_c) of PBS and nylon11 phases in the blends with and without Joncryl ADR-4300.

3.6. Thermal Stability Analysis of Neat PBS and PBS/Nylon11 Blends by TGA

Table 3 presents thermal degradation temperatures (T_d) of neat PBS and PBS/nylon11 blends, which Figure 11 compares the first and the second derivative (DTG) curves of these materials as a function of nylon11 content. It was seen that neat PBS and neat nylon11 showed only one-step thermal degradation with the T_d at 345.9°C and 412.7°C, respectively. For the PBS/nylon11 blends, there were two thermal degradation steps that correlated to the thermal degradation of PBS and nylon11 separately. For melt blending without Joncryl ADR-4100, it was found that the $T_{d,PBS}$ was reduced with the increase of nylon11 content. The reduction of $T_{d,PBS}$ implied the decrease of PBS molecular weight during the melt blending with nylon11.




Fig. 11. Degradation temperatures of neat PBS and the PBS/nylon11 blends with and without Joncryl ADR-4300.

The thermal degradation of PBS was discussed extensively in the work by Rizzarelli *et al.* [12]. Thermo-oxidation process causes a significant reduction of the molecular weight of the polyesters, promoting the formation of PBS oligomers with different end groups. These newly formed end groups with hydroxyl or carboxylic acid end groups could interact with the adjacent molecules as known as the transesterification reaction. When Joncryl of 0.5 wt% was added into the melt blending, the $T_{d,PBS}$ increased with the PBS content of 10-20 wt%, and then sharply dropped with the nylon11 content of 30-50 wt%. This confirmed the role of Joncryl ADR-4300 to initiate the chain extension reaction with

PBS or nylon11 molecules. The chemical reaction scheme between epoxide groups of Joncryl ADR-4300 and hydroxyl end groups in the PBS or nylon11 molecules is proposed as shown in Fig. 12. When the epoxide groups of Joncryl ADR-4300 reacted with the hydroxyl or the carboxylic end groups between two PBS molecules, it extended the molecular chains of PBS. In contrast, when the epoxide groups reacted with the amide groups in PBS polymers, the PBS molecules would also be broken into two fragments causing the reduction of molecular weights.

Table 3. Thermal degradation temperatures of neat PBS and the PBS/nylon11 blends under nitrogen atmosphere.

Sample	1 st step degradation			2 nd step degradation		
	T_{onset} (°C)	T_{endset} (°C)	T_{max} (°C)	T_{onset} (°C)	T_{endset} (°C)	T_{max} (°C)
PBS	293.9	369.9	345.9	-	-	-
P9N1	302.8	376.9	348.8	398.8	415.9	410.9
P8N2	301.5	375.8	345.1	394.9	420.2	410.4
P7N3	309.0	376.5	345.5	404.4	417.5	411.7
P6N4	313.5	370.2	342.2	422.9	417.0	411.6
P5N5	311.3	370.2	339.0	401.9	423.0	413.8
P9N1 0.5 phr	301.4	374.6	350.9	406.6	417.4	413.2
P8N2 0.5 phr	304.1	375.6	349.7	408.3	417.8	414.6
P7N3 0.5 phr	306.0	378.0	345.3	403.8	417.6	412.4
P6N4 0.5 phr	311.7	381.2	340.9	403.5	418.7	412.5
P5N5 0.5phr	313.2	388.3	334.4	395.0	427.2	414.5
P9N1 1.0 phr	302.0	366.2	345.0	390.1	419.3	413.0
P8N2 1.0 phr	301.9	375.8	347.2	405.7	417.3	413.1
P7N3 1.0 phr	307.1	379.6	346.9	399.2	416.9	413.1
P6N4 1.0 phr	311.5	382.6	343.3	401.1	417.6	413.6
P5N5 1.0 phr	314.0	379.7	342.6	408.5	416.9	413.2
Nylon11	389.9	432.5	412.7	-	-	-




Fig. 12. The chemical reaction scheme between epoxide groups of Joncryl ADR-4300 and hydroxyl end groups of PBS or nylon11 molecules.

4. Conclusion

The morphology of PBS/nylon11 blends indicated that they were immiscible blends which it was a sea-island structure when polyamide11 less than 50 wt%. Adding Joncryl ADR-4300 introduced better chemical compatibility in the blends evident by smaller dispersed domain sizes and less pullout. The blends with higher polyamide11 content had greater Young's modulus following the rule of mixture, however, the rigidity was reduced when adding the chain extender. The impact strength of the blends with polyamide11 content higher than 30 wt% was enhanced significantly with the presence of chain extender, although tensile strength and elongation at break were reduced. The crystallization temperature of PBS increased with higher polyamide11 content due to the nucleation effect, although the degree of crystallinity was in the same range. The thermal degradation temperature of the blend was shifted to higher temperature confirming the chain extension reaction occurred.

Acknowledgement

The research was funded and supported by the Department of Materials Science and Engineering, the Faculty of Engineering and Industrial Technology, Silpakorn University, Thailand.

References

- [1] K. Satish and K. S. Thakur, "Bioplastics - classification, production and their potential food applications," *Journal of Hill Agriculture*, vol. 8, no. 2, pp. 118-129, 2017.
- [2] R. Homklin and N., Hongsrirphan "Mechanical and thermal properties of PLA/PBS co-continuous blends adding nucleating agent," *Energy Procedia*, vol. 34, no. pp. 871-879, 2013.
- [3] Y.-D. Li, Q.-Q. Fu, M. Wang, and J.-B. Zeng, "Morphology, crystallization and rheological behavior in poly(butylene succinate)/cellulose nanocrystal nanocomposites fabricated by solution coagulation," *Carbohydrate Polymers*, vol. 164, no. pp. 75-82, 2017.
- [4] T. Moriyama, N. Sumiya, and T. Saito, "Impact strength improvement of polyamide 11 without flexural modulus reduction by dispersing poly(butylene succinate) particles," *Polymer Journal*, vol. 48, no. 2, pp. 221-224, 2015.
- [5] A. A. Tavares, D. F. A. Silva, P. S. Lima, D. L. A. C. S. Andrade, S. M. L. Silva, and E. L. Canedo, "Chain extension of virgin and recycled polyethylene terephthalate," *Polymer Testing*, vol. 50, pp. 26-32, 2016.
- [6] P. Raffa, M.-B. Coltelli, S. Savi, S. Bianchi, and V. Castelvetro, "Chain extension and branching of poly(ethylene terephthalate) (PET) with di- and multifunctional epoxy or isocyanate additives: An experimental and modelling study," *Reactive & Functional Polymers*, vol. 72, pp. 50-60, 2012.
- [7] Y. J. Phua, W. S. Chow, and Z. A. M. Ishak, "Reactive processing of maleic anhydride-grafted poly(butylene succinate) and the compatibilizing effect on poly(butylene succinate) nanocomposites," *eXPRESS Polymer Letters*, vol. 7, no. 4, pp. 340-354, 2013.
- [8] J. O. Fernandez, G. M. Swallowe, and S. F. Lee, "Crystallization of Nylon 11 under compressive high strain rates," *Journal of Applied Polymer Science*, vol. 80, no. 11, pp. 2031-2038, 2001.
- [9] M. L. D. Lorenzo, A. Longo, and R. Androsch, "Polyamide 11/poly(butylene succinate) bio-based polymer blends," *Materials*, vol. 12, no. pp. 2833-2846, 2019.
- [10] J. Zhou and B.G. Min, "Compatibilizing effect of epoxy resin on the phase separation and properties of polyamide 6/poly(ethylene terephthalate) blends," *Textile Science and Engineering*, vol. 51, no. 1, pp. 21-26, 2014.
- [11] S.-W. Kim, J.-C. Lim, D.-J. Kim, and K.-H. Seo, "Synthesis and characteristics of biodegradable copolyesters from the transesterification of poly(butylene adipate-co-succinate) and poly(ethylene terephthalate)," *Journal of Applied Polymer Science*, vol. 92, pp. 3266-3274, 2004.
- [12] P. Rizzarelli and S. Carroccio, "Thermo-oxidative processes in biodegradable poly(butylene succinate)," *Polymer Degradation and Stability*, vol. 94, pp. 1825-1838, 2009.



Nattakarn Hongsriphan is a full-time faculty in the position of associate professor at the Department of Materials Science and Engineering, Faculty of Engineering and Industrial Technology, Silpakorn University, Thailand. She was born at Sukhothai, Thailand in May 5, 1972. She graduated her bachelor's degree in Chemistry at Chiangmai University, Thailand (1997), and graduated her Doctor of Engineering in Plastics Engineering at the University of Massachusetts Lowell, USA (2003). She is the author of two books (in Thai language) and more than 40 journal articles. Her research interests include polymer blends, polymer composites, and polymer processing.



Chanasit Kaew-ngam was born in Nakhon Sawan, Thailand in May 7, 1996. He graduated bachelor's degree (1st degree honor) in Petrochemical and Polymeric Materials (2018) from the Department of Materials Science and Engineering, Faculty of Engineering and Industrial Technology, Silpakorn University, Thailand. He has pursued his doctoral degree in Chemical Technology at Chulalongkorn University, Thailand. His research interests in conversion of biomass to high-value chemicals and biofuels by heterogeneous catalysts.



Ploypailin Saengdet was born in Sakorn Nakhorn, Thailand in August 11, 1995. She graduated her bachelor's degree (1st degree honor) in Petrochemical and Polymeric Materials (2018) from the Department of Materials Science and Engineering, Faculty of Engineering and Industrial Technology, Silpakorn University, Thailand. She has pursued her doctoral degree at Vidyasirimedhi Institute of Science and Technology (VISTEC), Thailand. She was selected as the recipient of Srimedhi Scholarship that was granted by Her Royal Highness Princess Maha Chakri Sirindhorn in 2019. Her doctorate will have been earning under the direction of Professor Dr. Makoto Ogawa who is a council of International association for the study of clays (AIPEA). Her research interests include the synthesis and application of layered materials, calcium phosphate and polymer-clays

hybrids for bone tissue engineering.



Nisachon Kongtara was born in Nakhon Ratchasima, Thailand in September 18, 1995. She graduated her bachelor's degree (1st degree honor) in Petrochemical and Polymeric Materials (2018) from the Department of Materials Science and Engineering, Faculty of Engineering and Industrial Technology, Silpakorn University, Thailand. She is a master student under the supervision of Prof. Suwabun Chirachanchai at The Petroleum and Petrochemical College University, Thailand. Her research interests are focused on modification of membrane surface with CO₂-derived aliphatic polycarbonates used as polymer electrolyte in Li-ion battery.